

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

BEST AVAILABLE COPY

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.


Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Dated 15 January 2004

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)



The
Patent
Office

20DEC02 E772528-1 002835
P01/77 0 00-0229662.2

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form.)

The Patent Office

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference

P 203 202 / JDMA

2. Patent application number

(The Patent Office will fill in this part)

0229662.2

20 DEC 2002

3. Full name, address and postcode of the or of each applicant (underline all surnames)

UNIVERSITY OF NOTTINGHAM
NOTTINGHAM
NG1 2RD
8506437001
UNITED KINGDOM

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

4. Title of the invention

NANO STRUCTURES

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

URQUHART-DYKES & LIRD
TOWER HOUSE
MERRION WAY
LEEDS
LS2 8PA
164 4004

Patents ADP number (if you know it)

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:


YES

- a) ~~the~~ applicant named in part 3 is not an inventor, or
- b) ~~there is~~ an inventor who is not named as an applicant, or
- c) any named applicant is a corporate body.

See note (d)).

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document



Continuation sheets of this form

Description

0

8

Claim(s)

2

Abstract

1

Drawing(s)

0

10. If you are also filing any of the following, state how many against each item.

Priority documents

—

Translations of priority documents

—

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

—

Request for preliminary examination and search (Patents Form 9/77)

—

Request for substantive examination (Patents Form 10/77)

—

Any other documents (please specify)

—

11.

I/We request the grant of a patent on the basis of this application.

Signature

Dr JDM Atkinson

Date

20/12/02

12. Name and daytime telephone number of person to contact in the United Kingdom

Dr JDM ATKINSON

0113 245 2388

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Patents Form 1/77

NANOSTRUCTURES

The present invention relates to nanotubes and in particular to a process and apparatus for the preparation of nanotubes. More specifically, the present invention relates to nanotubes which are made from materials other than carbon or nanotubes containing carbon but which would not ordinarily be classed as carbon nanotubes on account of their low carbon content.

Carbon nanotubes are effectively cylindrical structures based on a hexagonal lattice of carbon atoms that forms crystalline graphite. Carbon nanotubes may have a single wall or a multi-walled structure. Carbon nanotubes can behave as a semiconductor or a metal depending on the diameter and arrangement of the graphitic rings in the walls.

Carbon nanotubes are thus unique nanostructures having unusual electronic and mechanical properties. Carbon nanotubes usually have a diameter in the order of 0.4 nanometres (nm) to 100 nm and a length of up to about 1 cm. Nanotubes can be considered as prototypes for one-dimensional quantum wire and these properties derive specifically from their structure. Groups of nanotubes can be joined together to form molecular wires. In effect, carbon nanotubes are a type of fullerene and the ends of carbon nanotubes must be formed from fullerene-like caps. This has the consequence that the diameter of a carbon nanotube can only be as small as a fullerene molecule.

The one-dimensional electronic properties of carbon nanotubes arise due to the quantum confinement of electrons in a direction normal to the nanotube axis. The result is that a number of one-dimensional conduction and valence bands are produced with most carbon nanotube structures being semiconducting and a small number being metallic in behaviour, depending on the diameter and arrangement of the hexagonal network of carbon atoms forming the nanotube.

There has been much anticipation regarding the potential interesting electrical, magnetic, non-linear-optical, thermal and mechanical properties of carbon nanotubes. Indeed, carbon

nanotubes exhibit mechanical strength and strain characteristics which are greater than those of steel and other alloys. At the same time, carbon nanotubes have a low density which is similar to or less than ceramic or polymeric materials of conventional types.

WO02/081366 describes a process for producing carbon nanotubes in which a substrate capable of supporting carbon nanotube growth is provided in a reaction chamber in the proximity of a heating element. Gaseous carbonaceous material is then passed into the reaction chamber so that it passes over and contacts the substrate with the result that the carbon nanotubes grow on the substrate. This process is said to allow the preparation of carbon nanotubes at temperatures as low as 300°C.

WO02/42204 discloses a process for preparing carbon nanotube composite structures and this patent attempts to overcome the problems of producing carbon nanotube composites with denser material such as metals, ceramics or polymer matrices. It is suggested that one problem in the production of such material stems from the fact that the density differences between the materials results in a gravitational separation of the composite materials from the lightweight carbon nanotubes. In addition, the electrostatic properties lead to the agglomeration of the carbon nanotubes during composite formation with the result that a homogeneous matrix of composite material cannot reliably be formed.

However, the prior art does not disclose any form of nanotube based either entirely or predominantly on material other than carbon. The interest in carbon nanotubes arises because of the possibility of allowing step changes in the performance of a wide range of systems. However, the number of applications of carbon nanotubes is limited by the range of structures and electronic properties available. The present invention aims to provide a wide range of nanoscale structures such as nanorods, nanofibres and nanotubes from ~~materials~~ other than carbon. It is also within the scope of the invention to produce ~~nanoscale~~ structures which incorporate carbon but which would not be classified as carbon nanostructures because of their low (ie less than 50% carbon content).

According to one aspect of the present invention there is provided a nanoscale structure formed from at least one element selected from groups IA and IIA of the periodic table and at least one element selected from groups IIIA, IVA, and VA.

In an embodiment, the nanostructure is inorganic.

Preferably, the element of group IA is lithium, sodium or potassium and, most preferably the element is lithium.

Preferably, the structure is a nanotube, nanorod or nanofibre. More preferably the structure is a nanotube.

In an embodiment, the non-metallic element selected from group IIIA, IVA, and VA is one or more of boron, carbon, silicon or nitrogen. Most preferably, the non-metallic element is nitrogen. Most preferably, the nanostructure is based on lithium nitride (Li_3N).

In the nanostructures of the present invention, it is possible to replace some or all of the metallic element of group IA and IIA with another element such as hydrogen or a transition metal, preferably copper, nickel, cobalt, iron, manganese and zinc, in order to modify the properties of the nanostructure. Thus a transitional metal or hydrogen may also optionally be present in the reaction vessel during formation of the nanostructure.

In another aspect of the present invention, the nanostructure is a nanotube in which the hollow core has been filled with another material such as a metal to form a metallic nanowire.

In a further embodiment of the present invention, chemical modification of the nanostructure may be performed in order to enhance or tailor the properties of the nanostructure. Thus, in the case of lithium nitride it is possible to oxidise partially the nanostructure either to produce a non-stoichiometric structure containing lithium, nitrogen and oxygen or to produce a nanostructure effectively based on lithium oxide.

In another aspect of the present invention, there is provided a process for the production of a nanostructure as defined previously, the process comprising exposing the metal of Group IA or IIA to a gaseous source of the element of Group IIIA, IVA, or VA, optionally in the presence of a transition metal, in a sealed heated chamber at a pressure between atmospheric pressure and a pressure of 10^{-4} torr, wherein the upper limit of the temperature is not more than 1200°C .

Preferably, in the process the upper limit of the temperature is defined by the temperature of decomposition of the compound.

In an embodiment, the process is used to make lithium nitride. In this case, lithium is heated in the presence of nitrogen in a sealed vessel until the pressure in the vessel is constant to form a lithium nitride nanostructure.

Inorganic nanostructures, such as those based on lithium nitride are expected to be of benefit in a number of applications on account of the number of different properties which are available from materials of this type. Thus, for example lithium nitride is a superionic conductor and nanostructures derived from lithium nitride therefore are likely to find application in materials such as rechargeable nano-batteries and other electronic components. This is one application for which carbon nanostructures are clearly unsuitable.

The nanostructures of the present invention have a number of applications such as: ionic conductors/battery components, in hydrogen storage devices, for templating nanowires, electrical devices, catalysis and synthesis, flat screen technology (display screens), and in mechanical applications as structural members. Inorganic nanostructures according to the present invention are capable of fulfilling all of these applications.

In the case of ionic conductors/battery components, modification of the lithium nitride nanostructure by the partial substitution of the group IA or IIA metal for another element such as cobalt, nickel, copper, iron, manganese or zinc etc lead to modulation of the electronic properties such as improved conductivity due to increased vacancy levels and

reduced activation energies. There are also improvements in stability of the structures. Accordingly, these materials will be ideally suitable for use as components in small rechargeable batteries. Thus, in one embodiment of this aspect of the invention unmodified lithium nitride forms the electrolyte and substituted lithium nitride nanostructures form the electrodes. Presently, there is no nanotube system which is capable of being an ionic conductor and thus capable of incorporation into a battery.

The inorganic nanotubes of the present invention are expected to show enhanced hydrogen storage capacity compared with carbon nanotube systems. Thus, in a further aspect of the present invention relates to the use of a nanotube structure based on an inorganic material, such as lithium nitride, to accommodate and store hydrogen within the structure. Such a structure containing hydrogen will also benefit from an improved ionic conductivity. This method of inclusion of hydrogen within the structure provides an alternative method of storing hydrogen rather than just in the form of absorbed molecules and is expected to find use in application where the ability to store a large volume of hydrogen is important. Examples of such use include advanced fuel cells for vehicles.

Although it has been shown to be possible to fill carbon nanotubes with metal in order to form metallic nanowire through the centre of the tube there is the problem that subsequent removal of the carbon nanotube template to release the nanowire requires harsh conditions. In contrast, the inorganic nanotubes of the present invention are easy to remove after filling with metal to form a nanowire as they may be decomposed under appropriate (mild) conditions in the presence of water or air. This represents a significant advantage relative to the more forcing conditions required in the case of carbon nanotubes. Thus another aspect of the invention relates to a nanowire derived from an inorganic nanotube.

The inorganic nanostructures of the present invention can also be used to form electronic devices. Conventional carbon nanotubes have been proposed as nanoscale components such as transistors. However, ionic conductors based on the inorganic nanostructures of the present invention offer an alternative for these systems. Thus, in the case of lithium nitride, the superionic conductivity and availability of a number of different valency bands

allows a range of conductivity properties to be exploited and thus a number of devices to be produced.

The nanostructures of the present invention also provide materials which can be used as catalysts in reactions. The nanostructure morphology such as catalysts formed into nanotubes or nanofilaments offer advantages over the use of powders in terms of the size, surface area and shapes selectivity of the active catalytic surface. The nanostructures of the present invention may be used either in their free form or when immobilised to a suitable substrate. In addition, the possibility of chirality in the nanostructure means that the catalysts may be used as chiral catalysts.

The electronic properties of inorganic nanostructures such as lithium nitride nanotubes also lead to an application in flat screen technology as emitting diodes (field emitting displays).

Certain of the inorganic nanostructures of the present invention display also extremely high tensile strengths along their length. Also, advantageous compressive properties and/or flexural properties (such as shear deformation) are seen in these materials. Thus, for example, lithium nitride nanotubes may be used as structural elements in certain devices.

Synthesis of the nanoscale structures can be achieved either directly or indirectly. The exact mechanism of the formation of the nanostructures of the present invention is not clear. However, a number of features are believed to be important in ensuring the formation of a nanostructure.

The shape and size of the reaction vessel is important. We have found that a long narrow shape is important in establishing a temperature gradient. Ideally the length of the vessel should be at least twice its diameter in order to ensure a favourable temperature gradient. Temperature gradients are particularly important in chemical vapour transport techniques for producing inorganic nanostructures such as those of the chalcogenides.

We have also found that the product only forms if the pressure is reduced below atmospheric pressure. However, we have also found that it is still necessary for there to be

a certain amount of gas present in the reactor vessel and it is believed that this behaves as a transport gas. There is, however, a lower limit to the pressure in the reaction vessel and we have found that the synthesis does not progress well below a pressure of 10^{-4} torr. The upper limit of the acceptable pressure range is atmospheric pressure.

It is also important that the temperature is sufficiently high that the inorganic compound becomes volatile. In the case of lithium nitride a suitable temperature range is between 150°C and 300°C depending on the pressure in the reaction vessel. The upper limit of the temperature is governed by the need to avoid decomposition of the inorganic compound, although some decomposition may be tolerated as it is believed that the individual elements may be transported and recombined in the vapour phase in certain inorganic compounds.

The presence of a transition metal in the reaction vessel during the formation of certain inorganic compounds has been found to be beneficial in producing the nanostructure or to alter the nature of the nanostructure. Thus, in the case of lithium nitride, the presence of iron powder in the reaction vessel leads to an alteration in the manner in which the sheets roll up. Thus, the presence of a transition metal may have a catalytic and/or structure directing effect in the formation of an inorganic nanostructure. In addition, there is the possibility of integrating (substituting) the transition metal into the walls of the inorganic nanostructure.

The present invention will now be illustrated with reference to the example of the preparation of an inorganic nanostructure based on lithium nitride. Lithium nitride can be formed by exposing lithium metal to nitrogen gas at room temperature. Alternatively, lithium can be heated in the presence of nitrogen. Lithium nitride can also be produced by using molten sodium as a solvent for lithium which is then reacted with nitrogen.

The dissolution of lithium in sodium is carried out in an argon-filled glove box and the sodium is kept molten using a hot plate to provide heating. The molten sodium keeps the argon atmosphere clean by reacting with any residual oxygen gas or water vapour which may be present. The lithium is dissolved in the molten sodium and the crucible containing

the mixture is then removed from the hot plate and allowed to cool. Once cool, the crucible is sealed in a reaction vessel in a furnace again in an argon gas atmosphere and heat and nitrogen are supplied. A clump of red fibrous material, consisting of lithium nitride nanotubes, grows above the crucible on a convenient surface provided within the furnace. Suitable surfaces include, for example, a loop of iron wire. The argon gas atmosphere is removed using a suitable pump and is replaced with nitrogen which is introduced under a positive pressure (typically 1.5 atmospheres). The reactants are heated to between 400 and 500°C, preferably about 460°C, for up to 72 hours and the pressure in the reaction vessel is monitored with a pressure transducer to measure pressure changes during the reaction. After a suitable period of time, usually between 6 and 72 hours, the reaction is complete and the point of completion can be measured by the pressure transducer. The pressure in the reaction vessel is constant once the reaction is complete and the vessel is then quenched to room temperature.

The reaction vessel includes a cold finger into which water is then placed and the vessel evacuated to a pressure of 10^{-4} torr or less. The vessel is again heated to between 400 and 500°C, preferably about 450°C, for up to 24 hours under a dynamic vacuum in order to distill off the sodium which recondenses on the cold finger. Lithium nitride in the form of a purple crystalline product remains in the crucible and may be collected.

-9-

Claims

1. A nanoscale structure formed from at least one element selected from groups IA and IIA of the periodic table and at least one element selected from groups IIIA, IVA, and VA.
2. A nanoscale structure as claimed in claim 1 wherein, the nanostructure is inorganic.
3. A nanoscale structure as claimed in claim 1, wherein the element of group IA is lithium, sodium or potassium.
4. A nanoscale structure as claimed in claim 3, wherein the element of Group IA is lithium.
5. A nanoscale structure as claimed in any preceding claim, wherein, the structure is a nanotube, nanorod or nanofibre.
6. A nanoscale structure as claimed in claim 5, wherein the structure is a nanotube.
7. A nanoscale structure as claimed in any of claims 1 to 6, wherein the non-metallic element selected from group IIIA, IVA, and VA is one or more of boron, carbon, silicon or nitrogen.
8. A nanoscale structure as claimed in claim 7, wherein the non-metallic element is nitrogen.
9. A nanoscale structure as claimed in any preceding claim in which some or all of the metallic element of group IA and IIA has been replaced with another element selected from hydrogen and/or a transition metal.

10. A nanoscale structure as claimed in any preceding claim, wherein the nanostructure is a nanotube in which the hollow core has been filled with a metal to form a metallic nanowire.
11. A nanoscale structure as claimed in any preceding claim, wherein chemical modification of the nanostructure has been performed in order to enhance or tailor the properties of the nanostructure.
12. A nanoscale structure based on lithium nitride (Li_3N).
13. Use of a nanostructure according to any of claims 1 to 12 in an ionic conductor/battery component, a hydrogen storage device, for templating nanowires, an electrical device, catalysis, a flat display screen, or as a structural member.
14. A process for the production of a nanostructure as defined in any of claims 1 to 12, the process comprising exposing the metal of Group IA or IIA to a gaseous source of the element of Group IIIA, IVA, or VA, optionally in the presence of a transition metal, in a sealed heated chamber at a pressure between atmospheric pressure and a pressure of 10^{-4} torr, wherein the upper limit of the temperature is not more than 1200°C .
15. A process as claimed in claim 14, wherein the upper limit of the temperature is defined by the temperature of decomposition of the compound.
16. A process as claimed in claim 14 or 15, wherein lithium is heated in the presence of nitrogen in a sealed vessel until the pressure in the vessel is constant to form a lithium nitride nanostructure.

Abstract

The present invention relates to nanotubes and in particular to a process and apparatus for the preparation of nanotubes. In particular, the present invention relates to nanotubes which are made from materials other than carbon or nanotubes containing carbon but which would not ordinarily be classed as carbon nanotubes on account of their low carbon content. The nanostructures of the present invention have a number of applications such as: ionic conductors/battery components, hydrogen storage, templating nanowires, electrical devices, catalysis and synthesis, flat screen technology, and mechanical applications.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.